
Electric & Communications



Specification Grade 1324



oldcastleprecast.com/enclosuresolutions

Oldcastle® Enclosure Solutions

Electric & Communications



Specification Grade

1324



Bolt Down Detail

L Bolt Detail

Raw Materia Specifications

Material Property	ASTM Test Method	Typical Value ¹	
Type, Class, Category	D 1248	III, A, 3	
Density, g/cm ³	D 1505	0.950 min., not to exceed 0.965	
Tensile Strength, at break, psi	D 638	3,000 to 4,400	
Elongation, at break, %	D 638	400	
Tensile Impact, ft-lb/in ²	D 1822	27	
Flexural Modulus, psi	D 790	120,000 min., not to exceed 240,000	
Low Temperature Brittleness, F50, at °C	D 746	<-76	
Hardness, Shore D	D 2240	66	
Deflection Temperature, at 66 psi, °F	D 648	150° min., not to exceed 200°	
Electrical Dielectric Strength, V/mil	D 149	400 min., not to exceed 600	
Molded Product			
Chemical Resistance	D 543	Very Resistant	
Water Absorption	D 570	Less than 1% weight change	

¹The values listed for physical property measurements are nominal values only. Certain physical property measurements are subject to variations consistent with the test methods and are within a generally accepted range for such values.

Product Load Rating:



Note:

Actual load rating is determined by the box and cover combination. Weights and dimensions may vary slightly All information contained on this sheet is current at the time of printing. Oldcastle Precast, Inc. reserves the right to discontinue or update product information without notice.



oldcastleprecast.com/enclosuresolutions